

SOLVENT RECYCLER PLASTIC BAGS INFORMATIONS

TECHNICAL DATA SHEET*	
Description	Value
Tensile Strength at Yield	10.9 psi
Elongation at Fail	170 %
Elongation at Break	9 %
Secant Modulus	435 psi
Melting point (DSC)	493°F / 256°C
Deflection Temperature at 66 psi	450°F / 232°C
Deflection Temperature at 264 psi	180°F / 82°C
Specific Gravity	1.14
Yield for 1.0 mil, sq. in./lb.	24.287
Continuous Use Temperature	450°F / 232°C
Material thickness	2 mil
Color	Green tint
Size	Many different sizes are available
Resistant	To most solvents

*Values reported for 0.2% moisture.

